



ART 34 AMDT

New Claims:

1. The use of a UV absorber for stabilizing inanimate organic materials against the action of light, the UV absorber comprising a finely divided polymer with a volume-average particle size of from 5 to 1 000 nm which contains repeat units of the formula I and/or II



in which

X is NH, O or S,

A or A¹ and A² together with the carbon atoms to which they are bonded form an aromatic backbone with one to three fused benzene rings or a diaryl backbone which can carry one to three substituents chosen from carboxyl, alkyl, alkenyl, aryl, alkylaryl, alkoxy, halogen or nitro, or a polymer chain containing repeat units of the formula I and/or II,


Ar is a divalent aromatic radical with one to three fused benzene rings or a diaryl radical which can carry one to three substituents chosen from carboxyl, alkyl, alkenyl, aryl, alkylaryl, alkoxy, halogen or nitro.

2. The use as claimed in claim 1, where the polymer is obtainable by polycondensation of compounds of the formula IV and optionally V and VI,

ART 34 AMDT


20

5



IV

10



V




VI

15

in which

X, A, A¹, A² and Ar are as defined in claim 1, and the compound of the formula IV used is at least partially a compound of the formula III

20



III.

25

3. The use as claimed in claim 2, where the compound of the formula III is 5-amino-4-hydroxyisophthalic acid.

30

4. The use as claimed in claim 2 or 3, where the compound of the formula III is used in an amount of at least 1 mol%, based on the total amount of the compounds IV, V and VI.

35

5. The use as claimed in any of claims 2 to 4, where the chain extenders co-used are diamines and/or diols and/or the chain terminators used are monobasic aromatic carboxylic acids, o-amino(thio)phenols, o-phenylenediamines, monohydric alcohols and/or monoamines.


40

6. The use as claimed in any of the preceding claims, where the inanimate organic material is a molding composition.


45

ART 34 AMDT


21



5



10



in which

15 X, A, A¹, A² and Ar are as defined in claim 1,

and subsequent comminution of the resulting polymer to a volume-average particle size of from 5 to 1 000 nm.

20 7. The use as claimed in claim 6, where the molding composition is a polyolefin, polyester, polyamide, polyurethane, polycarbonate, impact-modified polystyrene or a mixture thereof.


25 8. The use as claimed in any of claims 1 to 5, where the inanimate organic material is a coating film.

9. The use of the UV absorber as defined in any of claims 1 to 5 as a light protection factor in cosmetic formulations.


30

10. A UV absorber comprising a finely divided polymer with a volume-average particle size of from 5 to 1000 nm which contains repeat units of the formula I and/or II

35



40



45




in which

X is NH, O or S,


5 A or A¹ and A² together with the carbon atoms to which they are bonded form an aromatic backbone with one to three fused benzene rings or a diaryl backbone which can carry one to three substituents chosen from carboxyl, alkyl, alkenyl, aryl, alkylaryl, alkoxy, halogen or nitro, or a
10 polymer chain containing repeat units of the formula I and/or II,

Ar is a divalent aromatic radical with one to three fused benzene rings or a diaryl radical which can carry one to three substituents chosen from carboxyl, alkyl, alkenyl, aryl, alkylaryl, alkoxy, halogen or nitro.
15

the polymer being obtainable by polycondensation of compounds of the formula IV and if appropriate V and VI,
20





and a compound of the formula III



being at least partially used as compound of the formula IV.
45

23

11. A UV absorber as claimed in claim 10, where the compound of the formula III is 5-amino-4-hydroxyisophthalic acid.
12. A UV absorber as claimed in claim 10 or 11, where the compound of the formula III is used in an amount of at least 1 mol%, based on the total amount of the compounds IV, V and VI.
13. A UV absorber as claimed in any of claims 10 to 12, where the chain extenders co-used are diamines and/or diols and/or the chain terminators used are monobasic aromatic carboxylic acids, o-amino(thio)phenols, o-phenylenediamines, monohydric alcohols and/or monoamines.
14. A process for the preparation of a UV-absorber as claimed in claim 10 by polycondensation of compounds of the formula IV and/or V and/or VI



in which

X, A, A¹, A² and Ar are as defined in claim 10.

15. A coating preparation comprising a UV absorber as claimed in any of claims 10 to 13.

16. A cosmetic formulation comprising a UV absorber as claimed in any of claims 10 to 13 and optionally cosmetically active ingredients in a cosmetically acceptable carrier.

ART 34 AMEND

24

17. A molding composition comprising a UV absorber as claimed in any of claims 10 to 13.

5

10

15

20

25

30

35

40

45